



MATEX
Leader of Textile Screen Printing Inks

PREPARATION AND USAGE OF ECOLOGICAL DISCHARGE INKS

- 1-Place 1 kg Discharge Transparent Base or Discharge White Base into a suitable container
- 2-For excellent high fastness the pigments to be added should not exceed 6%
- 3-Pigments choosed should be able to discharge
- 4-Place %6 ratio –(for 1kg it will be 60gr) activator powder into the prepared ink
- 5-Activator should be mixed in the ink thoroughly until dissolves
- 6- If you want your prepared colour to have more covering or for hard discharge fabric, Discharge White Base and Discharge Transparent Base can be mixed to a specific ratio
- 7-At 180-190 °C_drying specification is 2-2,5 minutes. Unsuccessful drying will create wash fastness problems
- 8- **204 ECO TS DISCHARGE TRANSPARENT** is formulated to design discharge effects by mixing with activator powder .It gives brightness colours , softer touch and a brilliant exceptional **on the fabrics which are easily suitable to the process discharge**
- 9- **202 ECO DISCHARGE TRANSPARENT** is formulated to design discharge effects by mixing with activator powder .It gives brightness colours , softer touch and a brilliant exceptional **on the fabrics which resist to the process discharge**